



大恭化學工業股份有限公司

TAH KONG CHEMICAL INDUSTRIAL CORP.

7TH FLOOR 778, PA TE ROAD, SEC.4,

TAIPEI, REPUBLIC OF CHINA

台北市八德路四段七七八號

新砂谷大樓七樓

TEL:(02)7859081-7

TLX:25217 TKCPIGMENT

CABLE:TKCHEMIAL TAIPEI

FAX:(02)7850907

## Master Batch for Light Fastness PP Fiber

1. **Description:** TPM is the processed pigment that is designed for PP Fiber coloration. This product has good dispersion, physical properties and coloration. It is suitable for PP Fiber maker and other related applications. Especially for the fibers that request for high weather resistance.

2. **Appearance:** Master Batch

3. **Product Properties:**

TPM color was conducted according to the light fastness of AATCC16E 1200hrs. The rating of CIBA Grey Scale is higher than 4 and its heat resistance is around 260°C ×5mins.

4. **Product Code:**

Item Code	Color
TPM Yellow 0Y191	Yellow (Greenish)
TPM Yellow 0Y173	Yellow (Reddish)
TPM Yellow 0Y190	Yellow (Reddish)
TPM Orange 1Y031	Orange
TPM Red 2Y273	Red (Yellowish)
TPM Red 2Y288	Red (Yellowish)
TPM Red 2Y290	Red
TPM Red 2Y287	Red (Bluish)
TPM Red 2Y289	Red (Bluish)
TPM Brown 3Y117	Brown

5. **Recommended Dosage:** 2~4% depends on the customers' conditions and requirements.

The above data and results are based on controlled or lab work and must be confirmed by buyer by testing for the intended conditions of use.

品名

M/B:4.0PHR

M/B:2.0PHR  
TEM WH 8A334:2.0PHR

TPM  
Yellow 0Y191


TPM  
Yellow 0Y173







TPM  
Yellow 0Y190

TPM  
Orange 1Y031

TPM  
Red 2Y273

TPM  
Red 2Y288



品名	M/B:4.0PHR	M/B:2.0PHR TEM WH 8A334:2.0PHR
TPM Red 2Y290		
TPM Red 2Y287		
TPM Red 2Y289		
TPM Brown 3Y117	